

Enhanced superconductivity in Hf–base metallic glasses

Emil Tafra¹, Mario Basletić¹, Ramir Ristić², Emil Babić¹ and Amir Hamzić¹

¹Department of Physics, Faculty of Science, P.O.Box 331, HR-10002 Zagreb, Croatia

²Department of Physics, University of Osijek, P.O.Box 125, HR-31000 Osijek, Croatia

Abstract. Systematic study of electrical resistivity of $\text{Hf}_{100-x}\text{Fe}_x$ ($x = 20, 25$), $\text{Hf}_{100-x}\text{Cu}_x$ ($x = 30, 40, 50$), and $\text{Ti}_{65}\text{Cu}_{35}$ metallic glasses has been done in the temperature range 0.3 K – 290 K, and in magnetic fields $B \leq 5$ T. All Hf–base alloys are superconducting with $T_c \geq 0.44$ K, which is well above T_c of pure crystalline Hf (0.13 K). From the initial slopes of the upper critical fields, $(dH_{c2}/dT)_{T_c}$, and resistivities we determined the dressed electronic densities of states, $N_\gamma(E_F)$, for all alloys. Both T_c and $N_\gamma(E_F)$ decrease with increasing x (Fe, Cu content). The results are compared with those for corresponding Zr–base metallic glasses and ion-implanted Hf films.

PACS numbers: 74.70.-b, 74.25.Op, 71.23.Cq, 74.81.Bd

Submitted to: *J. Phys.: Condens. Matter*

1. Introduction

Glassy TE–TL alloys (TE and TL being the early and late transition metal, respectively) have been extensively studied in recent decades [1] and the interest in these alloys further increased after the discovery of TE–TL base bulk metallic glasses [2, 3, 4]. These studies revealed several unusual phenomena [5, 6, 7, 8], which has lead to the development of novel concepts for the calculation of their properties [9, 10]. In TE–TL alloys the composition range for the formation of the amorphous state by rapid quenching from the melt is quite wide and in favourable cases it spans from 20 – 70 at. % of TL component. Such a broad composition range enables a detailed study of the changes in the electronic band structure and properties on alloying, through comparison between the model and experiment [1, 11, 12].

In nonmagnetic amorphous TE–TL alloys, several properties which are related to the electronic density of states (DOS) show simple, sometimes linear variation with TL content [1, 6, 7, 11, 12, 13, 14, 15, 16]. These simple variations of the properties correlate with ultraviolet photoemission spectroscopy (UPS) results for the same alloy systems [1, 17], which showed that DOS at the Fermi level (E_F), $N(E_F)$, is dominated by TE d-states. Accordingly, in amorphous TE–TL alloys, the effect of alloying with TL can be approximated with the dilution of amorphous TE [13]. So far, a majority of results on TE–TL alloys has been obtained for Zr–TL metallic glasses, rendering a comparison between alloy systems based on different TE (eg. Ti, Zr, Hf) rarely possible [11, 12, 18]. This is particularly true for superconductivity, with only a few results for superconducting transition temperatures T_c of Ti– [19] and Hf–base [20, 21] metallic glasses.

Here we report, to our knowledge first, systematic study of superconductivity in Hf–Fe and Hf–Cu metallic glasses. Our results show that the variation of T_c with x in $\text{Hf}_{100-x}\text{Fe}_x$ and $\text{Hf}_{100-x}\text{Cu}_x$ glassy alloys is quite similar to that observed in corresponding $\text{Zr}_{100-x}\text{Fe}_x$ and $\text{Zr}_{100-x}\text{Cu}_x$ metallic glasses [14, 15, 22]. In particular T_c decreases with x and the rate of decrease is much faster for $x = \text{Fe}$ than for Cu. The magnitudes of T_c in Hf–base alloys are about two times lower than those in corresponding Zr–base alloys [14, 15, 22]. The dressed density of states at the Fermi level, $N_\gamma(E_F)$, also decreases with increasing x . Thus, superconductivity in Hf–base alloys is consistent with “split-band” electronic structure of glassy TE–TL alloys [1, 17, 20].

2. Experimental

$\text{Hf}_{100-x}\text{Fe}_x$ ($x = 20, 25$), $\text{Hf}_{100-x}\text{Cu}_x$ ($x = 30, 40, 50$), and $\text{Ti}_{65}\text{Cu}_{35}$ amorphous ribbons were prepared by melt spinning of master alloys with the predetermined concentration in either pure Ar [23] or He [24] atmosphere. The ribbons were typically 10 μm (Hf–Fe) and 20 μm (all other alloys) thick and their amorphousness was verified by X-ray diffraction [23, 25]. About 9 mm long samples for resistivity measurements were glued by GE-varnish on the sample holder of a ^3He cryostat inserted into 16/18 T superconducting

Table 1. Measured and calculated parameters for Hf-Fe and Hf-Cu metallic glasses. ρ is resistivity at 2 K, α is the temperature coefficient of resistivity, T_c is the superconducting transition temperature, $(dH_{c2}/dT)_{T_c}$ is the initial slope of the upper critical field, and $N_\gamma(E_F)$ is the dressed density of states obtained from (1).

Alloy	ρ ($\mu\Omega\text{cm}$)	α (10^{-4}K^{-1})	T_c (K)	$(dH_{c2}/dT)_{T_c}$ (kOe/K)	$N_\gamma(E_F)$ (states/eV atom)
Hf ₈₀ Fe ₂₀	206	-1.2	1.86	38	2.27
Hf ₇₅ Fe ₂₅	200	-2.0	1.12	35	2.14
Hf ₇₀ Cu ₃₀	206	-1.3	1.36	28.5	1.64
Hf ₆₀ Cu ₄₀	212	-1.2	0.82	26.1	1.40
Hf ₅₀ Cu ₅₀	210	-1.1	0.44	23.7	1.16

magnet. The current and voltage wires were glued with silver paste onto the samples. The resistivity measurements were performed by low frequency (22 Hz) ac method with rms current $I = 0.1$ mA in the temperature range 0.3 K–290 K in magnetic field $B \leq 5$ T, perpendicular to the broad surface of the ribbon and to the current direction. The temperature was measured with calibrated Cernox thermometer situated close to the samples. The resistivity was determined from the measurements of resistance, length, mass and density of samples [13, 14, 15]. Due to finite width of the silver paste contacts the uncertainty in the absolute resistivity values was about 5%. This uncertainty propagated into the values of the density of states $N_\gamma(E_F)$. Some data relevant to our samples are given in table 1.

3. Results and discussion

Figure 1 shows the variation of resistance with temperature for Ti₆₅Cu₃₅ and selected Hf-Cu, Fe glassy alloys. As is usual for glassy TE_{100-x}TL_x alloys with high resistivity ($\rho \geq 140 \mu\Omega\text{cm}$) [6, 13, 26] all our samples had negative temperature coefficients of resistivity (TCR). The literature values for resistivities and TCRs of corresponding Hf-Cu and Ti₆₅Cu₃₅ [6, 26] agree quite well with our results (table 1). In particular, our $T = 2$ K resistivities, $\rho(2\text{K})$, are a few percent higher than the room temperature resistivities, $\rho(290\text{K})$, of other authors [6, 26, 27].

Figure 2 shows the variations of normalized resistance $R(T)/R(2\text{K})$ with temperature below 2.5 K for all studied alloys. All Hf-Cu, Fe samples become superconducting within the explored temperature range ($T \geq 0.3$ K). Except for Hf₇₅Fe₂₅ alloy, all other samples show very narrow superconducting transitions with typical widths (from 0.1 to $0.9\rho(2\text{K})$) $\Delta T_c \leq 0.04$ K, which can be regarded as an indication of good quality (homogeneity) of studied samples [13, 14, 15, 20, 27]. The transition width for Hf₇₅Fe₂₅ alloy, $\Delta T_c \cong 0.14$ K, is somewhat larger but not unusual for amorphous alloys. As illustrated in figure 2 the resistive transition of this alloy became narrower in




Figure 1. Temperature dependence of normalized resistance for representative Hf-based metallic glasses and $\text{Ti}_{65}\text{Cu}_{35}$ amorphous alloy.




Figure 2. Resistive transitions for Hf-based metallic glasses. For $\text{Hf}_{75}\text{Fe}_{25}$ alloy transitions curves in magnetic field 0 and 0.5 T are shown.




Figure 3. Superconducting transition temperature T_c for Hf-base (closed symbols; our work) and Zr-base (open symbols; [14]) metallic glasses. Maximum T_c for Cu-ion implanted Ti (open star), Zr ($\diamond$), and Hf ($\blacklozenge$) films, [28] and for crystalline Zr ($\square$) and Hf ($\blacksquare$) [29] are also shown. Shaded area denotes temperatures unattainable in our experiment.

applied field, which allowed reliable determination of the variation of the upper critical field with temperature, $H_{c2}(T)$, also for this alloy. The values of superconducting transition temperatures (defined as midpoints of resistive transitions) are given in table 1. Sample $\text{Ti}_{65}\text{Cu}_{35}$ showed no sign of superconductivity down to 0.3 K, which is consistent with the reported $T_c \cong 0.06$ K for this alloy [19].

In figure 3 we compare the variations of zero-field T_c s with concentration x for our $\text{Hf}_{100-x}\text{Fe}_x$ and $\text{Hf}_{100-x}\text{Cu}_x$ alloys, with the literature results for Zr-Fe and Zr-Cu alloys [14, 15, 22]. Also shown are the maximum T_c s (i.e. the highest attainable T_c in given $\text{TE}_{100-x}\text{Cu}_x$ series) of presumably amorphous Ti-Cu, Hf-Cu and Zr-Cu thin films, obtained by low temperature ion implantation [28], which seem to extrapolate quite well the results for metallic glasses to lower Cu contents. Since there are no previous results for T_c of Hf-Fe,Cu glassy alloys, we can compare our results only with that for splat cooled $\text{Hf}_{70}\text{Ni}_{30}$ foil [20] with $T_c = 1.5$ K. Judging by the relation between T_c s of similar Zr-Ni and Zr-Cu alloys [12, 14, 15, 22], T_c of $\text{Hf}_{70}\text{Ni}_{30}$ alloy [20] is consistent with $T_c = 1.36$ K for our $\text{Hf}_{70}\text{Cu}_{30}$ alloy. The transition temperatures of pure crystalline (hcp) Zr and Hf (figure 3) are about an order of magnitude lower than maximum T_c s of Zr-Cu and Hf-Cu amorphous alloys. This is qualitatively consistent with the observed [1, 12, 16, 17] and calculated [11, 12] higher $N(E_F)$ in dilute amorphous TE-TL alloys than those of pure crystalline (hcp) TE metals. As seen from figure 3 the variations of T_c with x in Zr-Fe,Cu and Hf-Fe,Cu amorphous alloys are qualitatively very similar, the main difference is that T_c s of Hf-Fe,Cu alloys are about two times lower than those




Figure 4. Upper critical field H_{c2} of representative Hf-based metallic glasses. See text for definition of H_{c2} .

of corresponding Zr-Fe,Cu alloys. Like in Zr-base alloys the rate of decrease of T_c with x in Hf-base alloys is much faster for Fe than for Cu alloy. This is due to onset of magnetic correlations such as the spin fluctuations and/or formation of magnetic moments/clusters which cause strong pair-breaking [14, 15, 20, 25].

Lower T_c s of Hf-Fe,Cu alloys, compared to those of Zr-Fe,Cu, are consistent with a decrease of $N(E_F)$ on going from Zr to Hf (due to the increase of the bandwidth), but may also be affected [29] by the different Debye temperatures of Zr- and Hf-base alloys. Unfortunately, there are no measurements of the low temperature specific heat (LTSH) of Hf-base metallic glasses [12] which are necessary in order to explain the difference between T_c s of Zr-base and Hf-base alloy systems. In the absence of LTSH, useful information about nature of superconductivity in metallic glasses can be obtained from the measurements of upper critical field $H_{c2}(T)$ [14, 15, 20, 21, 22, 27, 30]. The variation of H_{c2} with temperature in TE-TL metallic glasses is usually well described by the Werthamer-Helfand-Hohenberg theory [31] and a fit of experimental results to the model enables one to determine the spin-orbit interaction parameter, λ_{so} , and the Maki paramagnetic limitation parameter α [32]. However, such fits yield reliable results for the above parameters (especially λ_{so}) only if the measurements extend to sufficiently low temperature, $T/T_c \leq 0.1$ [21]. The $H_{c2}(T)$ variations for our Hf-Fe,Cu alloys are shown in figure 4. H_{c2} was defined with $0.9\rho(2K)$, but – as illustrated for $Hf_{80}Fe_{20}$ alloy – the variation of H_{c2} with T for $0.5\rho(2K)$ criterion was virtually the same. Due to low T_c s of alloys we have studied, our measurements are limited to $T/T_c \geq 0.2$ which is not sufficient for the accurate estimate of both λ_{so} and α . Instead, we can use rather well defined initial slopes of H_{c2} , $(dH_{c2}/dT)_{T_c}$, for our alloys (table 1) in order to estimate

their dressed densities of states, $N_\gamma(E_F)$ [14, 15, 20, 22, 27]. $N_\gamma(E_F)$ can be calculated from [31]:

$$N_\gamma(E_F) = -\frac{\pi M}{4k_B N_A \rho d} \left(\frac{dH_{c2}}{dt} \right)_{t=1}, \quad (1)$$

where k_B is Boltzmann constant, N_A the Avogadro number, M the molecular weight, d the mass density, and $t = T/T_c$. The product ρd can be expressed via resistance R , length l , and mass m of the sample, $\rho d = (mR/l^2)$ [14, 15, 27]. The values of $N_\gamma(E_F)$ for Hf-Cu,Fe alloys calculated by using (1) decrease with increasing Fe,Cu content (table 1) in the same fashion as $N_\gamma(E_F)$ in corresponding Zr-Fe,Cu alloys [14, 15]. However, the magnitudes of $N_\gamma(E_F)$ in Hf-base alloys are some 10–12% lower than those in corresponding Zr-base alloys [14, 15]. As in Zr-base alloys [14, 15, 20] a clear correlation exists between the values of $N_\gamma(E_F)$ and T_c . In metallic glasses the values of $N_\gamma(E_F)$ calculated from (1) usually agree well with those obtained more directly from the coefficient of a linear term in LTSH, γ [12, 14, 15, 20, 21, 22, 27, 30]:

$$N_\gamma(E_F)_{\text{LTSH}} = \frac{3\gamma}{\pi^2 k_B^2}. \quad (2)$$

The dressed density of states is enhanced by many body interactions in respect to a band (bare) density of states, $N(E_F)$. In particular, $N_\gamma(E_F) = (1 + \lambda_{\text{ep}} + \lambda_{\text{esf}})N(E_F)$, where λ_{ep} and λ_{esf} are the electron-phonon and electron-spin fluctuations interaction parameters, respectively. Since our Hf-base alloys were paramagnetic [25] with magnetic susceptibilities well below of those for corresponding Zr-base alloys [14, 15] we expect λ_{esf} to be small for Hf-Fe, and negligible for Hf-Cu alloys. For a reliable estimate of λ_{ep} the LTSH measurements are required [12]. Since at present no LTSH results for Hf-base glassy alloys exist [12] we cannot make accurate estimates of $N(E_F)$ for studied alloys.

In amorphous TE-TL alloys the electron-phonon enhancement factor can also be estimated from the temperature variation of the thermopower, $S(T)$ [6]. Such an estimate for amorphous Hf₅₀Cu₅₀ alloy yields $N_\gamma(E_F)/N(E_F) \cong 1.4$, nearly the same as that obtained for Zr₅₀Cu₅₀ alloy [33]. Another estimate of λ_{ep} in Hf-Cu glassy alloys can be obtained by dividing our results for $N_\gamma(E_F)$ with the calculated values of $N(E_F)$ for amorphous Hf_{100-x}Cu_x alloys [12, 34]. The ratio between our $N_\gamma(E_F)$ and (interpolated) values of $N(E_F)$ decreased from about 1.4 ($x = 30$) to $\cong 1.2$ ($x = 50$). This calculation gave $N(E_F)$ values for amorphous Hf-Cu alloys about 10% lower than the values of $N(E_F)$ in corresponding Zr-Cu alloys [12].

In principle, λ_{ep} can also be obtained from the approximate proportionality between λ_{ep} and $N(E_F)$ derived for disordered transition metal alloys of a given series [35] which was found applicable to several 4d (Zr,Mo)-base metallic glasses [20]. There, the coefficient of λ_{ep} vs. $N(E_F)$ variation for 4d and 5d series was found to be quite similar [35], whereas that for 3d series was sizeably smaller. This result is in qualitative agreement with the estimates of λ_{ep} from $S(T)$ [33] for equiatomic Ti-Cu, Zr-Cu and Hf-Cu amorphous alloys. Thus, the electron-phonon enhancement in Hf-Cu glassy alloys is probably quite similar to that in Zr-Cu alloys and the main reason for lower

T_c s in the former system may be higher ionic mass of Hf (lower Debye temperature, Θ_D [36]) and lower $N(E_F)$ [12].

Near absence of superconductivity in Ti-base metallic glasses [12, 19], also confirmed by us (figures 2 and 3), is puzzling. Since in these systems both $N_\gamma(E_F)$ and Θ_D are higher than those in corresponding Zr-base and Hf-base metallic glasses [12], an inefficient electron-phonon coupling is required to explain their low T_c s [34].

4. Conclusion

The first systematic study of superconductivity in Hf-based metallic glasses has been reported. A clear correlation between the values of T_c and the dressed density of states $N_\gamma(E_F)$ has been established. With exception of Hf₇₅Fe₂₅ alloy, higher $N_\gamma(E_F)$ corresponds to higher T_c . More rapid suppression of T_c with x in Hf_{100-x}Fe_x alloys than in Hf_{100-x}Cu_x is probably caused by magnetic effects. In general, the variations of T_c and $N_\gamma(E_F)$ in Hf-Fe,Cu metallic glasses with Fe,Cu content are qualitatively the same as those in corresponding Zr-Fe,Cu glassy alloys which is consistent with very similar electronic structures of these alloys. Considerably lower values of T_c in Hf-based metallic glasses than those in corresponding Zr-based alloys are probably due to the lower Debye temperatures Θ_D , and electronic densities of states $N(E_F)$ in former system. For a more detailed insight into the superconductivity of Hf-based metallic glasses the additional measurements of the low temperature specific heat (yielding Θ_D) and perhaps tunnelling experiments (giving more directly electron-phonon coupling) are required.

Acknowledgments

The samples Hf₇₀Cu₃₀ and Hf₆₀Cu₄₀ have been prepared by Dr. L. Varga and Dr. I. Bakonyi from Research Institute for Solid State Physics and Optics, Hungarian Academy of Sciences. This work was supported by the Croatian Ministry of Science, Education and Sports projects Nos. 119-1191458-1023 and 119-1191458-1019.

References

- [1] Beck H and Güntherodt H J (eds) 1994 *Glassy Metals III (Topics in Applied Physics vol 72)* (Berlin: Springer)
- [2] Peker A and Johnson W L 1993 *Appl. Phys. Lett.* **63** 2342
- [3] Das J, Tang M B, Kim K B, Theissmann R, Baier F, Wang W H and Eckert J 2005 *Phys. Rev. Lett.* **94** 205501
- [4] Inoue A, Zhang W, Zhang T and Kurosaka K 2001 *Acta Materialia* **49** 2645
- [5] Gey W, Eschner W and Yu M Galperin 1993 *Phys. Rev. B* **48** 15666
- [6] Howson M A and Gallagher B L 1988 *Phys. Reports* **170** 265
- [7] Marohnić Ž, Babić E, Guberović M and Morgan G 1988 *J. Non-Cryst. Solids* **105** 303
- [8] Whang S H, Polk D E and Giessen B C 1982 *4th Int. Conf. On Rapidly Quenched Metals* ed Masumoto T and Suzuki K (Sendai) p 1365
- [9] Jank W, Ch Hausleitner and Hafner J 1991 *Europhys. Lett.* **16** 473
- [10] Ch Hausleitner and Hafner J 1990 *Phys. Rev. B* **42** 5863

- [11] Mankovsky S, Bakonyi I and Ebert H 2007 *Phys. Rev. B* **76** 184405
- [12] Bakonyi I 1995 *J. Non-Cryst. Solids* **180** 131
- [13] Babić E, Ristić R, Miljak M, Scott M G and Gregan G 1981 *Solid State Commun.* **39** 139
- [14] Altounian Z and Strom-Olsen J O 1983 *Phys. Rev. B* **27** 4149
- [15] Batalla E, Altounian Z and Strom-Olsen J O 1985 *Phys. Rev. B* **31** 577
- [16] Ristić R and Babić E 2007 *Mater. Sci. Eng. A* **449-451** 569
- [17] Oelhafen P, Hauser E and Güntherodt H J 1979 *Solid State Commun.* **35** 1017
- [18] Bakonyi I 2005 *Acta Materialia* **53** 2509
- [19] Hickey B J, Greig D and Howson M A 1986 *J. Phys. F: Met. Phys.* **16** L13
- [20] Tenhover M and Johnson W L 1983 *Phys. Rev. B* **27** 1610
- [21] Nordström A, Dahlborg U and Rapp Ö 1993 *Phys. Rev. B* **48** 12866
- [22] Samwer K and v Lohneysen H 1982 *Phys. Rev. B* **26** 107
- [23] Revesz A, Cziraki A, Lovas A, Padar J, Ledvai J and Bakonyi I 2005 *Z. Metallkd* **96** 874
- [24] Babić E, Butcher S, Day R K and Dunlop J B 1985 *5th Int. Conf. On Rapidly Quenched Metals* ed Steeb S and Warlimont H (Amsterdam: Elsevier Science Publishers B.V.) p 1157
- [25] Pajić D, Zadro K, Ristić R, Živković I, Skoko Ž and Babić E 2007 *J. Phys.: Condens. Matter* **19** 296207
- [26] Pavuna D 1985 *Solid State Commun.* **54** 771
- [27] Karkut M G and Hake R R 1983 *Phys. Rev. B* **28** 1396
- [28] Meyer J D and Stritzker B 1983 *Z. Phys. B – Condensed Matter* **54** 25
- [29] Collings E W and Ho J C 1971 *Phys. Rev. B* **4** 349
- [30] Poon S J 1983 *Amorphous Metallic Alloys* ed Luborsky F (London: Butterworths) p 432
- [31] Werthamer N R, Helfand E and Hohenberg P C 1966 *Phys. Rev.* **147** 295
- [32] Maki K 1966 *Phys. Rev.* **148** 362
- [33] Gallagher B L and Hickey B J 1985 *J. Phys. F: Met. Phys.* **15** 911
- [34] Cyrot-Lackmann F, Mayou D and Nguyen Manh D 1988 *Mater. Sci. Eng.* **99** 245
- [35] Dynes R C and Varma C M 1976 *J. Phys. F: Met. Phys.* **6** L215
- [36] McMillan W L 1968 *Phys. Rev.* **157** 331